



PERFORMANCE DATA COMPARISONS

Monolithic Glass

Clear Float Glass

Product		VLT	LR	SHGC	LSG
Krystal Klear	6 mm	91%	8%	0.91	1.00
Clear	6 mm	88%	8%	0.84	1.05
Linea Azzurra	19 mm	81%	7%	0.66	1.23

Performance values are based on representative production samples and product modeling data using LBNL Window 7.3 software. Actual values may differ based on variations in the manufacturing process. For more information, please visit us.agc.com or contact Technical Services 888-234-8380. Environmental conditions based on NFRC 100-2010. Argon data based on 10% air and 90% argon. Thermal stress analysis or building codes may determine the requirement for heat-treated glass. Contact AGC Technical Services to ensure the correct form of glass to be supplied. For additional glass configurations use our AGC Glass Calculator. Performance data is subject to change and the most accurate data will be reflected in the Glass Calculator.